

BARITE ANALYSIS

Parameters	Results %	Method
BaSO ₄	97.31	TS EN 15309
LOI	0.060	
SO ₃	31.43	
Al ₂ O ₃	<0.010	
CaO	0.10	
MgO	0.27	
Fe ₂ O ₃	0.032	
Na ₂ O	0.41	
SiO ₂	0.066	
SrO	2.56	
BaO	65.07	
Cr ₂ O ₃	<0.010	
K ₂ O	<0.010	
MnO	<0.010	
P ₂ O ₅	<0.010	
TiO ₂	<0.010	

- Mineral Density: 3.9 – 4.2 – 4.4 – 4.6 gr/ml
- It will be shipped from our own barite mine in Turkey.
- Production is carried out in the desired dimensions.
- Production is carried out at the desired tonnage.